

TC41 INFUSION RTM MOULD SPRAY ADHESIVE

DATA SHEET

TensorGrip



As part of our **COMPOSITES** range, TC41 is a mist spray adhesive suitable for fibreglass infusion. It is also ideal for use in FRP/GRP applications as well as thick and thin fabric.

PRODUCT DESCRIPTION

TensorGrip® TC41 is designed for the infusion mould market. This is a high performance, solvent-based polymer adhesive in a pressurised canister delivery system. TensorGrip® TC41 is specifically designed to hold reinforcing fibres in place during the infusion process, without affecting the finished surface or mould. TensorGrip® TC41 combines super tack and long open time to make large flat, less demanding applications be completed with minimal time waste.

ADVANTAGES

- Used for Infusion/Vacuum Forming composites.
- High tack.
- Fine mist spray.
- Does not interfere with cure process.
- Long open time
- Low VOC
- Repositionable

DIRECTIONS FOR USE

- This product is designed to be applied to one of the surfaces to be bonded together. It can also be applied to both surfaces if required. Applying adhesives to both sides may be required when bonding core foams and balsa core materials. Make sure that surfaces are clean, dry and free from dirt, dust, oil, loose paint, wax or grease, etc. For best results, the temperature of the adhesive and the surfaces being bonded should be between 60 °F - 80 °F (16 °C - 27 °C).
- Use with adequate ventilation. When possible we recommend shaking the canister or aerosol well before using. When using a canister, attach and secure hose tightly onto the spray gun with required tip. Attach the other end of the hose onto the canister. Make sure the hose-valve connections are securely tight. Open the valve on the canister slowly and fully, check for leaks during this process. Unlock the trigger on the spray gun to start spraying.
- Spray about 10-20 cm (4" - 8") away at a 90 degree angle to the surface, applying a uniform, even coat of adhesive to obtain 80% to 100% coverage of the surface. If necessary, spray another coat of adhesive in areas that appear to need

more adhesive. If using a two way stick, spray both surfaces to be bonded, one surface vertically and the other surface horizontally. Allow the adhesive to tack off until no adhesive transfers to the knuckle when touched.

- Adhere surfaces and press together with adequate pressure.
- If the spray tip clogs, unscrew the spray tip from the gun and clean with solvent such as lacquer thinner or acetone. Do not use a pin on the spray tip orifice.

CANISTER STORAGE/CHANGE OVER

- Turn valve on canister into the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister. Reconnect the spray hose to a canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean. If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.

gößl  pfaff

www.goesl-pfaff.de

Gössl & Pfaff GmbH · Münchener Straße 13 · 85123 Karlskron/Brautlach · Telefon 0 84 50.9 32-0 · Fax 9 32-13 · E-Mail info@goesl-pfaff.de

TC4 INFUSION RTM MOULD SPRAY ADHESIVE

DATA SHEET

Tensor

SPECIAL PRECAUTIONS

For optimum results store canister above 18°C during use, but must always be above 10°C. Allow substrates to acclimatise to normal room temperature (18°C) for 48 hours before bonding. Do not exceed open time of the adhesive. Keep canister off cold concrete floors during use. If adhesive is expelled wet or as a jet, canister is too cold – move to warm environment and allow to thoroughly acclimatise before reusing.

CAUTION

- Use only in well ventilated areas.
- DO NOT thin or reactivate with solvents.
- DO NOT incinerate.
- DO NOT expose to extreme heat over 50°C.
- Keep away from sources of ignition.
- Release pressure before disconnecting hose.
- Test for suitability before use.

MSDS and Technical Data Sheets **MUST** be read and understood before use. Information contained in this technical literature is believed to be accurate and offered in good faith for the benefit of the consumer. The company however cannot assume any liability or risk involved in the use of its chemical products since the conditions of use are beyond our control. Statements concerning the possible use of our products are not intended as recommendations to infringe on any patent.

CHEMICAL TECHNICAL DATA

TYPICAL PROPERTIES

- | | |
|-------------------------------|--|
| • Total Solids: | 28-30% |
| • System flammability: | Adhesive in flammable solvent & propellant |
| • Shear: | Not determined |
| • Tensile: | Not determined |
| • Shear adhesion failure temp | Not determined |
| • (SAFT): | Not determined |
| • Heat Resistance: | Not determined |
| • Dry Time: | 3-5 mins dependant on temperature and humidity |
| • Open Time: | < 60 mins |
| • SHELF LIFE: | 18 months from date of manufacture |

PACKAGING

- | | |
|---------|---|
| • 6kg | Mini X canister suitable for industrial use only |
| • 11kg | Large canister suitable for industrial use only |
| • 500ml | Aerosol - Suitable of industrial and general public use |

STORAGE

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- Do Not store at temperatures over 50°C.
- Avoid exposure to direct sunlight.
- Do Not store directly on concrete floor.
- For optimum performance, store at 18°C during use, but must always be above 10°C.
- When connected, keep valve open and hose pressurised at all times.
- Do Not close valve until ready to connect to new cylinder.
- Release pressure in hose before disconnection.
- Always test product to determine suitability for your particular application prior to use in production.

DISCLAIMER OF WARRANTY: The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or additional findings that result from technological progress or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to verify that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use. If they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product, our guarantee applies within the context of the statutory regulations, and provisions in force. Current professional standards and in accordance with the regulations set out in our general sales conditions. The information detailed in the present technical data sheets is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

gößl  pfaff

www.goessl-pfaff.de

Gössl & Pfaff GmbH · Münchener Straße 13 · 85123 Karlskron/Brautlach · Telefon 0 84 50.9 32-0 · Fax 9 32-13 · E-Mail info@goessl-pfaff.de