

Sheet Wax 266

brown / 138 °C

Sheet Wax 266 were developed for the following uses:

To simulate metal or part thickness in construction of metal forming dies

To create two part molds requiring uniform thickness such as resin transfer molds (RTM)

Compatible with casting & laminating resin requiring or giving off heat during curing.

PHYSICAL SPECIFICATIONS		
Colour		Medium Brown
Thickness Tolerance	+/- "	0.002
Heat resistance	°C	138
Ash Content	%	0.117
Volumetric Expansion (68–86 °C)	%	0.2
Flexibility		Maximum

DELIVERY FORM

Description	PU	Article number
Sheet Wax 266 brown 138 °C		6wp266
0,25 mm	10 sheets	
0,4–0,7 mm	10 sheets	
0,75 mm	8 sheets	
0,8–1,0 mm	8 sheets	
1,25 mm	8 sheets	
1,5 mm	8 sheets	
2,0 mm	8 sheets	
2,5 mm	6 sheets	
3,0–4,0 mm	4 sheets	
5,0 mm	3 sheets	

HANDLING PRECAUTION

For further information, please consult the product safety data sheet.

Safety data sheets are deposited on our Homepage under shop.goessl-pfaff.de with the respective product.

INFORMATION

The information contained in this technical data sheet result from research and tests conducted in our Laboratories under precise conditions. It is the responsibility of the user to determine the suitability of Gößl + Pfaff GmbH products, under their own conditions before commencing with the proposed application. Gößl + Pfaff GmbH guarantee the conformity of their products with their specifications but cannot guarantee the compatibility of a product with any particular application. Gößl + Pfaff GmbH disclaim all responsibility for damage from any incident which results from the use of these products. The responsibility of Gößl + Pfaff GmbH is strictly limited to reimbursement or replacement of products which do not comply with the published specifications.