

Wax Release Spray GP

Release agent for UP-/EP-/PU-resins

Wax Release Spray GP is a fast-drying release agent in spray form with a very large range of application in the mould-making industry.

Suitable for the construction of aircrafts, gliders, boats, models, sport equipment, for polyester- and epoxy-resins, Polymethacrylatharze, PU masses as well as silicone rubber.

Also suitable for PMMA systems.

- excellent separating effect
- free of CFC propellants
- silicone-free
- fast-drying
- temperature resistance up to 90 °C



PHYSICAL SPECIFICATIONS			
Composition			Aerosol; active substances with propane/butane
Colour			milky white
Density at 20 °C	g/cm ³	DIN 51757	0.645

PROCESSING INSTRUCTIONS

**** Shake WELL before use!! ****

Spray the Wax Release Spray GP slowly and evenly onto the component or mould from 20 to 30 cm.

After flash-off (10 to 20 minutes), the release film can be polished with a soft clean cloth (cotton). (Caution: Friction generates heat. The release film should not be polished away!).

Do not apply excessive pressure when using polishing machines.

Polishing usually results in shiny surfaces.

The release agent should be brought to room temperature before use! Wax Release Spray GP should only be applied to cold surfaces!

New moulds and components must be waxed several times with wax release agent to seal/close the micropores before the first moulding.

Release agent builds up in the mould when used several times.

The release agent film can be carefully removed from the mould with solvent ([Chemlease® Mold Cleaner 1009W Art.-Nr.: 8tcc200](#)) and fine steel wool.

PREPARATION OF THE SURFACES

Tooling boards (Ureol), lacquered surfaces, EP, polyester top coats and resins, PU fast cast resins as well as 2C-lacquers.

The surfaces to be treated must be clean and free of grease, oil and silicone.

Absorbent substrates must be pre-treated with a release agent prior to treatment.

FORM OF DELIVERY

Description	PU	Article number
Wax Release Spray GP	400 ml Can	8t010.01
	12 x 400 ml Can	8t010.12

HANDLING PRECAUTIONS

Safety Datasheets/product info: <https://shop.goessl-pfaff.de/art/8t010>

Pressurized container. Protect from sunlight and temperatures above 50 °C.

Do not pierce or burn, even after use.

Do not spray on an open flame or hot surfaces.

Keep away from ignition sources. - No smoking.

May form explosive mixtures without sufficient ventilation.

Keep out of reach of children.

STORAGE

Wax Release Spray GP should be stored at temperatures between +10 °C and +30 °C.
Storage time: approx. 6 months in unopened original containers.

NOTE

The information contained in this technical data sheet result from research and tests conducted in our Laboratories under precise conditions. It is the responsibility of the user to determine the suitability of Gößl & Pfaff GmbH products, under their own conditions before commencing with the proposed application. Gößl + Pfaff GmbH guarantee the conformity of their products with their specifications but cannot guarantee the compatibility of a product with any particular application. Gößl + Pfaff GmbH disclaim all responsibility for damage from any incident which results from the use of these products. The responsibility of Gößl + Pfaff GmbH is strictly limited to reimbursement or replacement of products which do not comply with the published specifications.