

ELASTOSIL[®] C 1200 A/B

ELASTOSIL[®]

Room Temperature Curing Silicone Rubber (RTV-2)

Room temperature vulcanizing, addition-curing, two component silicone rubber (to be processed via brushing, spraying, casting).

System for the production of reusable silicone vacuum bags.



Properties

- low viscosity
- shear thinning
- good mechanical properties
- rapid curing
- easily remoldable

Specific features

- Addition-curing
- Fast curing
- No shrinkage
- Two-component

Technical data

Properties Uncured

| Property | Condition | A | B | Method |
|--------------------|-----------|------------------------|------------------------|----------|
| Color | - | transparent | blue | - |
| Density | 23 °C | 1.05 g/cm ³ | 1.05 g/cm ³ | ISO 2811 |
| Viscosity, dynamic | 23 °C | 20000 mPa·s | 20000 mPa·s | ISO 3219 |

These figures are only intended as a guide and should not be used in preparing specifications.

Catalyzed

| Property | Condition | Value | Method |
|------------------|-----------|--------------------|--------|
| Color | - | blue / translucent | - |
| Mix ratio | - | 1 : 1 | A : B |
| Pot life | - | 20 min | - |
| Demoldable after | - | 60 min | - |

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Vulcanizate after 24 h at 23 °C

| Property | Condition | Value | Method |
|---------------------|-----------|---------------------|--------------|
| Color | - | blue/translucent | - |
| Hardness Shore A | - | 25 | ISO 868 |
| Tensile strength | - | 5 N/mm ² | ISO 37 |
| Elongation at break | - | 500 % | ISO 37 |
| Tear strength | - | 25 N/mm | ASTM D 624 B |

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Composite molding

Application details

ELASTOSIL® C 1200 A/B has been especially developed for the professional production of reusable vacuum bags, used for the production of composite parts. Due to its shear thinning behavior it will be self leveling, yet not running off vertical surfaces.

It's medium term pot-life will allow the use on larger surfaces, still enabling a quick curing of the bag.

Processing

ELASTOSIL® C 1200 A/B may be processed using a manual or pneumatic gun. It is supplied in a double cartridge and will be applied directly onto the tool.

For larger amounts it may also be processed using a 2-component mixing and metering machine.

On larger surfaces it may also be sprayed using compressed air.

We recommend to post-curing the vacuum bag for 2-3 hours at operating temperature, 220 °C max.

Important note:

The platinum catalyst is in **component A**.

Caution:

Only components A and B with the same lot number may be processed together!

Please check also our brochures and info sheets.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Components A and B of the addition-curing grade ELASTOSIL® C 1200 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® C 1200 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.