

ELASTOSIL® M 4670 A/B

RTV-2 SILICONE RUBBER / MOLD MAKING

Product description

Pourable, addition-curing, two-component silicone rubber that vulcanizes at room temperature.

Special features

- good flow
- fast and non-shrink cure at room temperature which can be accelerated considerably by the application of heat
- high Shore A hardness (approx. 55)
- high tear strength
- long-term stability of the vulcanizate's mechanical properties
- outstanding resistance to common casting resins

Application

Due to its outstanding resistance to casting resins as well as its superior mechanical properties ELASTOSIL® M 4670 A/B is perfectly suitable for all molds of models with undercuts that are to be reproduced in casting resins, and a certain inherent rigidity of the molds is required.

As a medium-Shore addition-curing RTV-2 silicone rubber that cures without undergoing dimensional shrinkage, ELASTOSIL® M 4670 A/B is also extremely suitable for casting all other common reproduction materials, particularly if absolutely accurate copies of models with undercuts are required.

Processing

Important note:
The platinum catalyst is in component A.

Important:
A and B components may only be used together if they

have the same batch number.

Comprehensive instructions are given in our leaflet "ELASTOSIL® - PROCESSING RTV-2 SILICONE RUBBERS".

Detailed information on other mold-making compounds in the ELASTOSIL® M range is contained in our brochure "ELASTOSIL® M. Mold-Making Compounds For Maximum Precision".

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Additional information

Please visit our website www.wacker.com.

Safety notes

Components of the addition-curing grade ELASTOSIL® M 4670 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

Product data**Typical general characteristics****Inspection Method****Value****Product data (uncured)****Component A**

Color		beige
Density at 23 °C		1,32 g/cm ³
Viscosity at 23 °C, after stirring	ISO 3219	120000 mPa s

Component B

Color		colorless
Density at 23 °C		1,03 g/cm ³
Viscosity at 23 °C, after stirring	ISO 3219	7000 mPa s

Product data (catalyzed A + B)

Mix ratio (pbw)	A : B	10 : 1
Viscosity at 23 °C	ISO 3219	80000 mPa s
Pot life at 23 °C, up to 150000 mPa s		90 min
Cure time, non-adhesive		12 h

Product data (cured)

Color		beige
Density at 23 °C in water	ISO 2781	1,28 g/cm ³
Hardness Shore A	ISO 868	55
Tensile strength	ISO 37	5,50 N/mm ²
Elongation at break	ISO 37	250 %
Tear strength	ASTM D 624 B	> 12 N/mm
Linear shrinkage		< 0,1 %

Vulcanizate after 24 h at 23 °C

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER is a trademark of Wacker Chemie AG.
ELASTOSIL® is a trademark of Wacker Chemie AG.

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG
Hanns-Seidel-Platz 4
81737 München, Germany
info.silicones@wacker.com

www.wacker.com